



Mechanical alloying and milling

C. Suryanarayana

*Department of Metallurgical and Materials Engineering, Colorado School of Mines, Golden,
CO 80401-1887, USA*

Abstract

Mechanical alloying (MA) is a solid-state powder processing technique involving repeated welding, fracturing, and rewelding of powder particles in a high-energy ball mill. Originally developed to produce oxide-dispersion strengthened (ODS) nickel- and iron-base superalloys for applications in the aerospace industry, MA has now been shown to be capable of synthesizing a variety of equilibrium and non-equilibrium alloy phases starting from blended elemental or prealloyed powders. The non-equilibrium phases synthesized include supersaturated solid solutions, metastable crystalline and quasicrystalline phases, nanostructures, and amorphous alloys. Recent advances in these areas and also on disordering of ordered intermetallics and mechanochemical synthesis of materials have been critically reviewed after discussing the process and process variables involved in MA. The often vexing problem of powder contamination has been analyzed and methods have been suggested to avoid/minimize it. The present understanding of the modeling of the MA process has also been discussed. The present and potential applications of MA are described. Wherever possible, comparisons have been made on the product phases obtained by MA with those of rapid solidification processing, another non-equilibrium processing technique. © 2001 Elsevier Science Ltd. All rights reserved.

Contents

1. Introduction	3
2. Historical perspective.	6

E-mail address: schallap@mines.edu (C. Suryanarayana).

3.	Nomenclature	9
4.	The process of mechanical alloying	11
4.1.	Raw materials	11
4.2.	Types of mills	13
4.2.1.	SPEX shaker mills	13
4.2.2.	Planetary ball mills	15
4.2.3.	Attritor mills	15
4.2.4.	Commercial mills	18
4.2.5.	New designs	18
4.3.	Process variables	21
4.3.1.	Type of mill	21
4.3.2.	Milling container	22
4.3.3.	Milling speed	22
4.3.4.	Milling time	23
4.3.5.	Grinding medium	23
4.3.6.	Ball-to-powder weight ratio	24
4.3.7.	Extent of filling the vial	25
4.3.8.	Milling atmosphere	25
4.3.9.	Process control agents	26
4.3.10.	Temperature of milling	29
5.	Mechanism of alloying	32
5.1.	Ductile–ductile components	35
5.2.	Ductile–brittle components	37
5.3.	Brittle–brittle components	38
6.	Characterization of powders	39
7.	Temperature rise during milling	43
8.	Solid solubility extensions	45
8.1.	Difficulties in solid solubility determination	46
8.2.	Mechanisms of solid solubility extension	56
8.3.	Comparison between mechanical alloying and rapid solidification	60
9.	Synthesis of intermetallics	62
9.1.	Quasicrystalline phases	64
9.2.	Crystalline intermetallic phases	65
9.2.1.	Metastable crystalline phases	65
9.2.2.	High-pressure phases	69
9.2.3.	Equilibrium crystalline phases	75
9.3.	Refractory compounds	82
10.	Disordering of intermetallics	86
11.	Solid-state amorphization	95
11.1.	Thermodynamics and kinetics of amorphous phase formation	112

11.2.	Mechanism of amorphization	114
11.3.	Theoretical predictions of amorphous-phase-forming range.	116
11.4.	Comparison between mechanical alloying and rapid solidification	119
12.	Nanostructured materials	122
13.	Mechanochemical synthesis	125
13.1.	Process parameters	129
13.1.1.	Milling temperature.	129
13.1.2.	Ball-to-powder weight ratio	130
13.1.3.	Process control agent.	130
13.1.4.	Relative proportion of the reactants	131
13.1.5.	Grinding ball diameter	131
13.2.	Phase formation	132
13.3.	Combustion reaction	134
13.4.	Mechanosynthesis of compounds and composites.	134
14.	Powder contamination	136
15.	Modeling studies and milling maps	144
15.1.	Modeling studies	145
15.2.	Milling maps.	146
16.	Applications of mechanical alloying	150
16.1.	Nickel-base alloys	152
16.2.	Iron-base alloys.	155
16.3.	Aluminum-base alloys	157
16.4.	Magnesium-base alloys	158
16.5.	Other applications.	158
17.	Safety hazards.	159
18.	Concluding remarks	159
	Acknowledgements.	162
	References	162

1. Introduction

Scientific investigations by materials scientists have been continuously directed towards improving the properties and performance of materials. Significant improvements in mechanical, chemical, and physical properties have been achieved through chemistry modifications and conventional thermal, mechanical, and thermomechanical processing methods. However, the ever-increasing demands for “hotter, stronger, stiffer, and lighter” than traditional materials have led to the

3. Nomenclature

Two different terms are commonly used in the literature to denote the processing of powder particles in high-energy ball mills. *Mechanical Alloying* (MA) describes the process when mixtures of powders (of different metals or alloys/compounds) are milled together. Material transfer is involved in this process to obtain a homogeneous alloy. On the other hand, milling of uniform (often stoichiometric) composition powders, such as pure metals, intermetallics, or prealloyed powders, where material transfer is not required for homogenization, has been termed *Mechanical Milling* (MM). The destruction of long-range order in intermetallics to produce either a disordered intermetallic or an amorphous phase has been referred to as *Mechanical Disordering* (MD) [51]. The advantage of MM/MD over MA is that since the powders are already alloyed and only a reduction in particle size and/or other transformations need to be induced mechanically, the time required for processing is short. For example, MM requires half the time required for MA to achieve the same effect [52]. Additionally, MM of powders reduces oxidation of the constituent powders, related to the shortened time of processing [52]. Some investigators have referred to MM as *Mechanical Grinding* (MG). Since “grinding” is normally thought of as an abrasive machining process that involves mainly shear stresses and chip formation, the term “milling” is preferred to include the more complex triaxial, perhaps partly hydrostatic, stress states that can occur during ball milling of powders [5]. It should also be realized that MA is a generic term, and some investigators use this term to include both mechanical alloying and mechanical milling/disordering/grinding. However, we will distinguish between these two terms by using MA or MM depending on whether material transfer is involved or not during processing.

Some other terms are also used in the literature on Mechanical Alloying. These include reaction (or reactive ball) milling, cryomilling, rod milling, mechanically activated annealing (M2A), double mechanical alloying (dMA), and mechanically activated self-propagating high-temperature synthesis (MASHS).

Reaction Milling (RM) is the mechanical alloying process accompanied by a solid-state reaction and was pioneered by Jangg et al. [53]. In this process the powder is milled without the aid of any process control agent (see later for its function during milling) to produce fine dispersions of oxides and carbides in aluminum [54]. The dispersion of carbides is achieved by adding lamp-black or graphite during milling of aluminum. Adjusting the oxygen content via close control of the milling atmosphere (oxygen, argon, nitrogen, air, etc.) produces the oxides. Thus, the final product of milling contains a dispersion of Al_4C_3 and Al_2O_3 in an aluminum matrix and these alloys are given the trade name DISPAL. Milling of metal powders in the presence of reactive solids/liquids/gases (enabling a chemical reaction to take place) is now regularly employed to synthesize metal oxides, nitrides, and carbides [55,56]. Thus, milling of titanium in a nitrogen atmosphere has produced titanium nitride [57,58]. Several other compounds have also been produced in a similar way. Milling of tungsten with carbon (graphite) has produced tungsten carbide [59]. Milling of metal powders with boron has